# Prima-160 Stretch

53% COTTON / 44% POLYESTER / 3% SPANDEX

160 GSM / TWILL 2/1

ULTRA SOFT*

| | |
|---|---|
| Fabric name | Prima-160 Stretch |
| Fabric weight | 160 ± 5 gsm |
| Composition | 53% Cotton, 44% Polyester, 3% Spandex |
| Full width | 150 ± 2 cm |
| Weave | twill 2/1 |
| Finishes | Peach |
| Area of use | Medical uniform, HoReCa uniform |
| Washing instruction | |

## Physical properties*

| | | | warp | weft |
|---|---|---|---|---|
| 1 | Tensile strength, N | ISO 13934-1:2013 | 1100 | 310 |
| 2 | Tearing strength, N | ISO 13937-3:2000 | 25 | 21 |
| 3 | Dimensional Stability To Washing 60°C, max | ISO 6330:2000 | 3.0% | 3.0% |
| 4 | Abrasion Resistance | ISO 12947-2:2002 | > 20 000 | |
| 5 | Pilling Resistance after 7000 revol. | ISO 12945-2:2000 | 4 | |
| 6 | Colour Fastness To Washing (cotton+polyester) 60°C, min. | ISO 105-C06:2010 | 4-5 | |
| | Colour change | ISO 105-C06:2010 | 4-5 | |
| | Colour staining to cotton | ISO 105-C06:2010 | 4-5 | |
| | Colour staining to polyester | ISO 105-C06:2010 | 4 | |
| 7 | Colour Fastness To Perspiration, min. | ISO 105-E04:2013 | | |
| | Colour change | | 4-5 | |
| | Colour staining | | 4-5 | |
| 8 | Colour Fastness To Rubbing, min. | ISO 105-X12:2001 | | |
| | Dry | | 4-5 | |
| | Wet | | 2 | |
| 9 | Colour Fastness To Light | ISO 105-B02:2013 | 4 | |

* The values shown are indicative and may vary slightly from batch to batch.

www.xmtextiles.com


**XM TEXTILES EUROPE**
Dariaus ir Gireno st. 42A, Room 509
Vilnius, LT-02189, Lithuania
Tel. +370 52 078 703
info@xmtextiles.com

**XM TEXTILES ROMANIA**
Sos.Tamasi 20, Hala 6B, Parter,
Buftea, 070000, Ilfov, Romania
Tel. +40 31 630 3639
info@xmtextiles.com

**XM TEXTILES ITALIA SRL**
Via dei Notai, Blocco 23, Centergross,
40050 Funo di Argelato (BO), Bologna, Italy
Tel. +39 051 952 8202
info@xmtextiles.com