



Flame Retardant fabric for FR-clothing

SONORA

80% COTTON / 20% POLYESTER

185 GSM / PLAIN 1/1



Fabric name	Sonora
Fabric weight	185 ± 10 gsm
Composition	80% Cotton / 20% Polyester
Full width	150 ± 2 cm
Weave	Plain 1/1
Finishes	Flame Retardant
Application	FR Lining
Washing instruction	

FR & SPECIAL PROPERTIES

Flame retardant	EN ISO 11612 A1, C1, F1	5×60°C ISO 6330
-----------------	-------------------------	-----------------

PHYSICAL PROPERTIES

		warp	weft
Tensile strength, N	ISO 13934-1:1999	750	550
Tearing strength, N	ISO 13937-2:2000	16	15
Dimensional Stability To Washing, max	ISO 5077	3%	
Abrasion Resistance	ISO 12947-2:1999	17,000 rubs	
Pilling Resistance	ISO 12945-2:2001	4	

COLOUR FASTNESS

			Light	Mid	Dark	Special
			Orange, Yellow	Green, Grey, Royal Box	Dark Navy, Navy, Royal Blue	Black
Wash Fastness Method E2S (95°C)	ISO 105-C06	Colour Change	4-5	4-5	4-5	4-5
		Stain on Polyester	4	4-5	4	4
		Stain on Cotton	4-5	4-5	4-5	4
Rub Fastness	ISO 105-X12	Wet	4	3	3	3
		Dry	4-5	4	4	4
Light Fastness	ISO 105-B02		3	4	4	4

www.xmtextiles.com

XM TEXTILES EUROPE

Dariaus ir Gireno st. 42A, Room 509
Vilnius, LT-02189, Lithuania
Tel. +370 52 078 703
info@xmtextiles.com

XM TEXTILES ROMANIA

Sos. Tamasi 20, Hala 6B, Parter,
Buftea, 070000, Ilfov, Romania
Tel. +40 31 630 3639
info@xmtextiles.com

XM TEXTILES ITALIA SRL

Via dei Notai, Blocco 23, Centergross,
40050 Fano di Argelato (BO), Bologna, Italy
Tel. +39 051 952 8202
info@xmtextiles.com