

Amber-225

55% COTTON / 42% POLYESTER / 3%
ELASTANE 200 GSM / SATIN 4/1



Fabric name	Amber-225
Fabric weight	225 ± 5 gsm
Composition	55% cotton, 42% polyester, 3% elastane
Full width	150 ± 2 cm
Weave	Satin 4/1
Finishes	-
Area of use	Beauty and Health industry
Washing instruction	

Physical properties*

			warp	weft
1	Tensile strength, N	ISO 13934-1:2013	1200	1100
2	Tearing strength, N	ISO 13937-3:2000	19	66
3	Dimensional Stability To Washing, max.	ISO 6330:2000	3.0%	3.0%
4	Abrasion Resistance	ISO 12947-2:2002	> 25 000	
5	Pilling Resistance (after 2000 rev.)	ISO 12945-2:2000	5	
6	Colour Fastness To Washing (cotton+polyester) 60°C, min.	ISO 105-C06:2010		
	Colour change	ISO 105-C06:2010	5	
	Colour staining	ISO 105-C06:2010	4-5	
7	Colour Fastness To Perspiration, min.	ISO 105-E04:2013		
	Colour change		5	
	Colour staining		4-5	
8	Colour Fastness To Rubbing, min.	ISO 105-X12:2001		
	Dry		4-5	
	Wet		4	
9	Colour Fastness To Light	ISO 105-B02:2013	4-5	

* The values shown are indicative and may vary slightly from batch to batch.

www.xmtextiles.com