



Flame Retardant fabric for FR-clothing

MADEIRA-320

100% COTTON

320 GSM / TWILL 3/1



Fabric name	Madeira-320
Fabric weight	320 ± 10 gsm
Composition	100% Cotton
Full width	152 ± 2 cm
Weave	Twil 3/1
Finishes	Flame Retardant
Application	FR jackets, trousers and coveralls
Washing instruction	

FR & SPECIAL PROPERTIES

Flame retardant	EN ISO 11612 (A1 & A2, B1, C1, F1 E3)	50×75°C ISO 15797
	EN ISO 11611 (Class 1)	50×75°C ISO 15797
	EN ISO 11612 (A1 & A2)	100×75°C ISO 15797
	EN 11612 D1	5×75°C ISO 15797

PHYSICAL PROPERTIES

		warp	
Tensile strength, N	ISO 13934-1:1999	1600	1000
Tearing strength, N	ISO 13937-2:2000	22	17
Dimensional Stability To Washing, max	ISO 5077	3%	
Abrasion Resistance	ISO 12947-2:1999	26,500 rubs	
Pilling Resistance	ISO 12945-2:2001	3-4	

COLOUR FASTNESS

			Light	Mid	Dark	Special
			Orange, Yellow, Red	Green, Grey, Royal Box	Dark Navy, Navy, Royal Blue	Black
Wash Fastness Method E2S (95°C)	ISO 105-C06	Colour Change	4-5	4-5	4-5	4
		Stain on Polyester	4-5	4-5	4	4
		Stain on Cotton	4	4	4	3-4
Rub Fastness	ISO 105-X12	Wet	3	3	2-3	2
		Dry	4	4	4	4
Light Fastness	ISO 105-B02		3	4	4	4

www.xmtextiles.com

XM TEXTILES EUROPE

Dariaus ir Gireno st. 42A, Room 509
Vilnius, LT-02189, Lithuania
Tel. +370 52 078 703
info@xmtextiles.com

XM TEXTILES ROMANIA

Sos.Tamasi 20, Hala 6B, Parter,
Buftea, 070000, Ilfov, Romania
Tel. +40 31 630 3639
info@xmtextiles.com

XM TEXTILES ITALIA SRL

Via dei Notai, Blocco 23, Centergross,
40050 Fano di Argelato (BO), Bologna, Italy
Tel. +39 051 952 8202
info@xmtextiles.com