

Topper-245 Stretch

65% POLYESTER / 32% COTTON / 3% EOL
245 GSM / TWILL 2/1



Fabric name	Topper-245 Stretch
Fabric weight	245 ± 5 gsm
Composition	65% Polyester, 32% Cotton, 3% EOL
Full width	152 ± 2 cm
Weave	Twill 2/1
Finishes	-
Area of use	heavy duty workwear
Washing instruction	

Physical properties*

			warp	weft
1	Tensile strength (after 50 ind. washes), N	ISO 13934-1:2013	1600	740
2	Tearing strength (after 50 ind. washes), N	ISO 13937-3:2000	32	30
3	Dimensional Stability To Washing, max.	EN ISO 15797:2018	3%	3%
4	Abrasion Resistance	ISO 12947-2:2002	> 100 000	
5	Pilling Resistance after 2000 revol.	ISO 12945-2:2000	4-5	
6	Colour Fastness To Washing (cotton+polyester) 75°C, min.	ISO 105-C06:2010		
	Colour change	ISO 105-C06:2010	4-5	
	Colour staining to cotton	ISO 105-C06:2010	4-5	
	Colour staining to polyester	ISO 105-C06:2010	4	
7	Colour Fastness To Perspiration, min.	ISO 105-E04:2013		
	Colour change		4-5	
	Colour staining		4-5	
8	Colour Fastness To Rubbing, min.	ISO 105-X12:2001		
	Dry		4-5	
	Wet		2-3	
9	Colour Fastness To Light	ISO 105-B02:2014	6	
10	PH level	EN ISO 3071:2020	6.95	

* The values shown are indicative and may vary slightly from batch to batch.
www.xmtextiles.com